

# MyFloor<sup>TM</sup> FILM + LAMINATE

The indoor floor decal solution



## Applications

INDOOR

WET  
AREAS

## Description

MyFloor is a new cost effective indoor floor decal solution comprising Film & Laminate. It can be applied easily, removed cleanly and comes with an R9 / P3 non-slip certification making it suitable for wet area's indoors.

## Features & Benefits

- Cost effective indoor floor decal solution
- Suitable for most indoor flat & smooth surfaces
- R9/P3 non-slip approved laminate suitable for indoor wet areas
- Thicker 240 micron non-slip approved laminate provides:
  - Longer durability, up to 12 months
  - Easier installation
- No fuss clean removal
- Excellent dimensional stability

## Applications

- Retail activations
- POS promotions
- Social distancing
- Directional messaging

## Surfaces

- > Tiles
- > Stone
- > Vinyl
- > Floorboards
- > Sealed smooth concrete

## Slip Resistance

R9 / P3 non-slip laminate suitable for indoor wet areas  
Australian / New Zealand standards AS 4586:2013

## Test First

Every surface is different and changes with time so we recommend trialling first with a small piece in a inconspicuous location. Trial over a minimum 4 week period to determine suitability for the intended

## Durability

MyFloor durability depends on many factors including the surface it is applied to and the frequency of abrasive forces. Please see guide below;

- > Low Traffic - 12 months
- > High Traffic - 3 months

## Technical Information

Size Width: 1.372m  
Length: 50m  
MyFloor Laminate 240 micron  
MyFloor Film printable on UV, Solvent & Latex

## Warranty

Since there is no control under which conditions the product has been applied or has been used, all product warranty automatically end as soon as the product has been applied to any surface

2 April 2020

## Test Report No. M0874

### Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586 and HB 198.

Requested by: Visionary Digital Pty Ltd.  
Client Address: Factory 2/27 William Street  
Balaclava VIC 3183  
Product Manufacturer: Continental Grafix  
Product Description: MyFloor Lam

Test conducted according to: AS 4586:2013 Appendix A  
Location: Level 1, 420 Spencer Street, West Melbourne VIC 3003  
Conducted by: Christopher McWilliam

Date:	01 April 2020	Temperature:	23 C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	N/A		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	37	43	42	41	41

<b>Reported SRV of Sample:</b>	<b>41</b>
<b>Class:</b>	<b>P3</b>



2 April 2020  
M0874 - Slip Check, MyFloor Lam

7 April 2020

# Test Report No. M0875

## Slip Resistance Classification of New Pedestrian Surface Materials

### AS 4586-2013 Appendix D (Oil-Wet Inclining Platform Test)

The slip resistance classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586 and HB 198.

Requested by: Visionary Digital Pty Ltd  
Client Address: Factory 2/27 William Street  
Balaclava VIC 3183  
Product Manufacturer: Continental Grafix  
Product Description: MyFloor Lam  
Surface Structure: Smooth  
Fixed/Unfixed: Fixed  
Joint Width: N/A  
Test conducted according to: AS 4586-2013 Appendix D (Incorporating Amendment No. 1)  
Location: 4/40 Bessemer Street, Blacktown NSW 2148  
Conducted by: Oshi Barkat & Connor Murphy  
Test Shoe Type: Bergmann with LeipzigV73-SP sole form  
Date: 07 April 2020  
Cleaning: As Received  
Air Temperature: 22 C  
Displacement Space: Not Measured  
Displacement Space Assessment Group: NA

<b>Corrected Mean Overall Acceptance Angle:</b>	<b>9°</b>
<b>Slip Resistance Assessment Group:</b>	<b>R9</b>

7 April 2020  
M0875 - Slip Check, MyFloor Lam